

Siliceous Material, CRM, Pottery Stone, only available as set, please see JCRM-R604-R605-R751, Powder

Art. ID JCRM-R751
Unit 50 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		2,73	%		
	Al ₂ O ₃		14,15	%		
	CaO		0,033	%		
	Fe ₂ O ₃		0,34	%		
	K ₂ O		~3	%		
	MgO	[1309-48-4]	0,049	%		
	MnO		0,003	%		
	Na ₂ O		0,121	%		
	P ₂ O ₅		0,009	%		
	Sulfur (S)	[7704-34-9]	~0,001	%		
	SiO ₂		79,32	%		
	TiO ₂		0,01	%		