

Siliceous Material, CRM, Prophyllite, only available as set, please see JCRM-R702-R703-R803, Powder

Art. ID JCRM-R803
Unit 50 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		4,4	%		
	Al ₂ O ₃		23,95	%		
	CaO		0,033	%		
	Fe ₂ O ₃		0,047	%		
	K ₂ O		2,32	%		
	MgO	[1309-48-4]	0,017	%		
	MnO		0,0014	%		
	Na ₂ O		0,165	%		
	P ₂ O ₅		0,018	%		
	Sulfur (S)	[7704-34-9]	0,02	%		
	SiO ₂		68,52	%		
	TiO ₂		0,104	%		