

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-121
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,05	%		
	Al ₂ O ₃		6,07	%		
	CaO		1,96	%		
	Cr ₂ O ₃		0,01	%		
	Fe ₂ O ₃		0,4	%		
	K ₂ O		0,23	%		
	MgO	[1309-48-4]	0,12	%		
	MnO		0,02	%		
	Na ₂ O		3,2	%		
	P ₂ O ₅		0,32	%		
	SiO ₂		86,3	%		
	TiO ₂		0,05	%		
	ZrO ₂		1,11	%		