

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-122
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,12	%		
	Al ₂ O ₃		10,2	%		
	CaO		0,43	%		
	Cr ₂ O ₃		0,81	%		
	Fe ₂ O ₃		0,24	%		
	K ₂ O		2,05	%		
	MgO	[1309-48-4]	0,65	%		
	MnO		0,2	%		
	Na ₂ O		1,04	%		
	P ₂ O ₅		4,89	%		
	SiO ₂		78,2	%		
	TiO ₂		1,03	%		
	ZrO ₂		0,2	%		