

**Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder**

Art. ID JRRM-123  
Unit 20 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,03	%		
	Al <sub>2</sub> O <sub>3</sub>		13,3	%		
	CaO		0,13	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,01	%		
	Fe <sub>2</sub> O <sub>3</sub>		4,13	%		
	K <sub>2</sub> O		0,1	%		
	MgO	[1309-48-4]	1,32	%		
	MnO		0,01	%		
	Na <sub>2</sub> O		0,29	%		
	P <sub>2</sub> O <sub>5</sub>		0,8	%		
	SiO <sub>2</sub>		79,1	%		
	TiO <sub>2</sub>		0,45	%		