

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-124
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Loss on Ignition (LOI) | | ~0,1 | % | | |
| | Al ₂ O ₃ | | 16,5 | % | | |
| | CaO | | 1,09 | % | | |
| | Cr ₂ O ₃ | | 0,11 | % | | |
| | Fe ₂ O ₃ | | 2,6 | % | | |
| | K ₂ O | | 1,79 | % | | |
| | MgO | [1309-48-4] | 0,1 | % | | |
| | MnO | | 0,24 | % | | |
| | Na ₂ O | | 0,31 | % | | |
| | P ₂ O ₅ | | 0,19 | % | | |
| | SiO ₂ | | 73,9 | % | | |
| | TiO ₂ | | 2,74 | % | | |
| | ZrO ₂ | | 0,11 | % | | |