

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-125
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,07	%		
	Al ₂ O ₃		18,7	%		
	CaO		0,13	%		
	Cr ₂ O ₃		0,01	%		
	Fe ₂ O ₃		0,5	%		
	K ₂ O		0,69	%		
	MgO	[1309-48-4]	0,08	%		
	Na ₂ O		0,07	%		
	P ₂ O ₅		0,04	%		
	SiO ₂		79,2	%		
	TiO ₂		0,3	%		
	ZrO ₂		0,02	%		