

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-127
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,07	%		
	Al ₂ O ₃		23	%		
	CaO		0,18	%		
	Cr ₂ O ₃		0,27	%		
	Fe ₂ O ₃		0,92	%		
	K ₂ O		0,54	%		
	MgO	[1309-48-4]	0,15	%		
	MnO		0,17	%		
	Na ₂ O		1,75	%		
	P ₂ O ₅		1,78	%		
	SiO ₂		68,5	%		
	TiO ₂		2,19	%		
	ZrO ₂		0,04	%		