

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-128
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,02	%		
	Al ₂ O ₃		26	%		
	CaO		2,8	%		
	Cr ₂ O ₃		0,85	%		
	Fe ₂ O ₃		4,45	%		
	K ₂ O		1,84	%		
	MgO	[1309-48-4]	3,1	%		
	MnO		0,24	%		
	Na ₂ O		0,37	%		
	P ₂ O ₅		3,36	%		
	SiO ₂		54,3	%		
	TiO ₂		1,37	%		
	ZrO ₂		1,01	%		