

**Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder**

Art. ID JRRM-129  
Unit 20 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,11	%		
	Al <sub>2</sub> O <sub>3</sub>		30,1	%		
	CaO		0,15	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,1	%		
	Fe <sub>2</sub> O <sub>3</sub>		1,46	%		
	K <sub>2</sub> O		1,92	%		
	MgO	[1309-48-4]	2,23	%		
	MnO		0,01	%		
	Na <sub>2</sub> O		0,23	%		
	P <sub>2</sub> O <sub>5</sub>		0,2	%		
	SiO <sub>2</sub>		62,2	%		
	TiO <sub>2</sub>		0,96	%		
	ZrO <sub>2</sub>		0,11	%		