

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-129
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,11	%		
	Al ₂ O ₃		30,1	%		
	CaO		0,15	%		
	Cr ₂ O ₃		0,1	%		
	Fe ₂ O ₃		1,46	%		
	K ₂ O		1,92	%		
	MgO	[1309-48-4]	2,23	%		
	MnO		0,01	%		
	Na ₂ O		0,23	%		
	P ₂ O ₅		0,2	%		
	SiO ₂		62,2	%		
	TiO ₂		0,96	%		
	ZrO ₂		0,11	%		