

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-130
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,11	%		
	Al ₂ O ₃		32,7	%		
	CaO		1,95	%		
	Cr ₂ O ₃		1,05	%		
	Fe ₂ O ₃		0,53	%		
	K ₂ O		1,42	%		
	MgO	[1309-48-4]	0,61	%		
	MnO		0,37	%		
	Na ₂ O		2,32	%		
	P ₂ O ₅		0,91	%		
	SiO ₂		53,4	%		
	TiO ₂		3,35	%		
	ZrO ₂		0,83	%		