

**Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder**

Art. ID JRRM-131  
Unit 20 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,17	%		
	Al <sub>2</sub> O <sub>3</sub>		36,6	%		
	CaO		0,78	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,07	%		
	Fe <sub>2</sub> O <sub>3</sub>		2,2	%		
	K <sub>2</sub> O		2,61	%		
	MgO	[1309-48-4]	1,02	%		
	MnO		0,03	%		
	Na <sub>2</sub> O		0,76	%		
	P <sub>2</sub> O <sub>5</sub>		1,61	%		
	SiO <sub>2</sub>		52,7	%		
	TiO <sub>2</sub>		1,16	%		
	ZrO <sub>2</sub>		0,26	%		