

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-132
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,15	%		
	Al ₂ O ₃		39,1	%		
	CaO		1,29	%		
	Cr ₂ O ₃		0,11	%		
	Fe ₂ O ₃		1,64	%		
	K ₂ O		0,79	%		
	MgO	[1309-48-4]	0,34	%		
	MnO		0,11	%		
	Na ₂ O		2,16	%		
	P ₂ O ₅		2,38	%		
	SiO ₂		50,6	%		
	TiO ₂		0,29	%		
	ZrO ₂		0,75	%		