

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-133
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,08	%		
	Al ₂ O ₃		39	%		
	CaO		0,1	%		
	Cr ₂ O ₃		1,27	%		
	Fe ₂ O ₃		3,69	%		
	K ₂ O		0,91	%		
	MgO	[1309-48-4]	2,03	%		
	MnO		0,01	%		
	Na ₂ O		0,33	%		
	P ₂ O ₅		0,34	%		
	SiO ₂		50,1	%		
	TiO ₂		1,93	%		
	ZrO ₂		0,57	%		