

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-134
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,14	%		
	Al ₂ O ₃		44,3	%		
	CaO		0,2	%		
	Cr ₂ O ₃		0,24	%		
	Fe ₂ O ₃		1,07	%		
	K ₂ O		0,37	%		
	MgO	[1309-48-4]	0,2	%		
	MnO		0,24	%		
	Na ₂ O		0,13	%		
	P ₂ O ₅		3,83	%		
	SiO ₂		47,2	%		
	TiO ₂		1,74	%		
	ZrO ₂		0,35	%		