

Refractory, CRM, Fireclay, only available as set, please see JRRM-121-135, Powder

Art. ID JRRM-135
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,18	%		
	Al ₂ O ₃		48,9	%		
	CaO		2,36	%		
	Cr ₂ O ₃		0,42	%		
	Fe ₂ O ₃		3,05	%		
	K ₂ O		2,77	%		
	MgO	[1309-48-4]	1,24	%		
	MnO		0,04	%		
	Na ₂ O		2,87	%		
	P ₂ O ₅		0,48	%		
	SiO ₂		37,2	%		
	TiO ₂		0,07	%		
	ZrO ₂		0,2	%		