

Refractory, CRM, Chrome Magnesia, only available as set, please see JRRM-501-512, Powder

Art. ID JRRM-504
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Loss on Ignition (LOI) | | ~0,12 | % | | |
| | Al ₂ O ₃ | | 17,56 | % | | |
| | CaO | | 2,6 | % | | |
| | Cr ₂ O ₃ | | 18,35 | % | | |
| | Fe ₂ O ₃ | | 4,11 | % | | |
| | MgO | [1309-48-4] | 54,85 | % | | |
| | MnO | | 0,01 | % | | |
| | NiO | | ~0,01 | % | | |
| | P ₂ O ₅ | | ~0,03 | % | | |
| | SiO ₂ | | 2,18 | % | | |
| | TiO ₂ | | 0,01 | % | | |
| | V ₂ O ₅ | | ~0,01 | % | | |
| | ZnO | | ~0,01 | % | | |