

**Refractory, CRM, Chrome Magnesia, only available as set, please see JRRM-501-512, Powder**

Art. ID JRRM-509  
Unit 20 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,13	%		
	Al <sub>2</sub> O <sub>3</sub>		20,28	%		
	CaO		2,86	%		
	Cr <sub>2</sub> O <sub>3</sub>		42,57	%		
	Fe <sub>2</sub> O <sub>3</sub>		10,15	%		
	MgO	[1309-48-4]	20,45	%		
	MnO		0,08	%		
	NiO		~0,04	%		
	P <sub>2</sub> O <sub>5</sub>		~0,01	%		
	SiO <sub>2</sub>		1,96	%		
	TiO <sub>2</sub>		1,2	%		
	V <sub>2</sub> O <sub>5</sub>		~0,11	%		
	ZnO		~0,03	%		