

**Refractory, CRM, Chrome Magnesia, only available as set, please see JRRM-501-512, Powder**

Art. ID JRRM-512  
Unit 20 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,02	%		
	Al <sub>2</sub> O <sub>3</sub>		29,25	%		
	CaO		4,06	%		
	Cr <sub>2</sub> O <sub>3</sub>		4,98	%		
	Fe <sub>2</sub> O <sub>3</sub>		26,01	%		
	MgO	[1309-48-4]	24,81	%		
	MnO		0,02	%		
	NiO		~0,01	%		
	P <sub>2</sub> O <sub>5</sub>		~0,01	%		
	SiO <sub>2</sub>		10,57	%		
	TiO <sub>2</sub>		0,04	%		
	V <sub>2</sub> O <sub>5</sub>		~0,01	%		
	ZnO		~0,01	%		