

Refractory, CRM, Zircon-Zirconia, only available as set, please see JRRM-601-610, Powder

Art. ID JRRM-601
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		0,11	%		
	CaO		5,58	%		
	Fe ₂ O ₃		0,1	%		
	HfO ₂		1,59	%		
	MgO	[1309-48-4]	0,06	%		
	SiO ₂		0,26	%		
	TiO ₂		0,16	%		
	ZrO ₂		92	%		