

**Refractory, CRM, Zircon-Zirconia, only available as set, please see JRRM-601-610, Powder**

Art. ID                      JRRM-602  
Unit                         20 g (powder)  
Deliverydetails            No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		0,07	%		
	CaO		0,22	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,01	%		
	Fe <sub>2</sub> O <sub>3</sub>		1,62	%		
	HfO <sub>2</sub>		1,52	%		
	MgO	[1309-48-4]	5,3	%		
	Na <sub>2</sub> O		0,76	%		
	P <sub>2</sub> O <sub>5</sub>		1,34	%		
	SiO <sub>2</sub>		0,33	%		
	TiO <sub>2</sub>		0,16	%		
	ZrO <sub>2</sub>		88,4	%		