

Refractory, CRM, Zircon-Zirconia, only available as set, please see JRRM-601-610, Powder

Art. ID JRRM-602
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		0,07	%		
	CaO		0,22	%		
	Cr ₂ O ₃		0,01	%		
	Fe ₂ O ₃		1,62	%		
	HfO ₂		1,52	%		
	MgO	[1309-48-4]	5,3	%		
	Na ₂ O		0,76	%		
	P ₂ O ₅		1,34	%		
	SiO ₂		0,33	%		
	TiO ₂		0,16	%		
	ZrO ₂		88,4	%		