

**Refractory, CRM, Zircon-Zirconia, only available as set, please see JRRM-601-610, Powder**

Art. ID JRRM-603  
Unit 20 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al <sub>2</sub> O <sub>3</sub>		5,29	%		
	CaO		0,95	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,02	%		
	Fe <sub>2</sub> O <sub>3</sub>		2,86	%		
	HfO <sub>2</sub>		1,45	%		
	K <sub>2</sub> O		0,65	%		
	MgO	[1309-48-4]	0,96	%		
	Na <sub>2</sub> O		0,18	%		
	P <sub>2</sub> O <sub>5</sub>		0,83	%		
	SiO <sub>2</sub>		0,96	%		
	TiO <sub>2</sub>		0,93	%		
	ZrO <sub>2</sub>		84,8	%		