

Refractory, CRM, Zircon-Zirconia, only available as set, please see JRRM-601-610, Powder

Art. ID JRRM-604
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		6,93	%		
	CaO		0,09	%		
	Cr ₂ O ₃		3,06	%		
	Fe ₂ O ₃		0,43	%		
	HfO ₂		1,35	%		
	K ₂ O		1,94	%		
	MgO	[1309-48-4]	0,01	%		
	Na ₂ O		1,09	%		
	P ₂ O ₅		1,99	%		
	SiO ₂		3,05	%		
	TiO ₂		0,13	%		
	ZrO ₂		79,4	%		