

Refractory, CRM, Zircon-Zirconia, only available as set, please see JRRM-601-610, Powder

Art. ID JRRM-605
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		4,84	%		
	CaO		1,94	%		
	Cr ₂ O ₃		1,55	%		
	Fe ₂ O ₃		0,17	%		
	HfO ₂		1,31	%		
	K ₂ O		0,54	%		
	MgO	[1309-48-4]	1,99	%		
	Na ₂ O		0,45	%		
	P ₂ O ₅		0,35	%		
	SiO ₂		10,8	%		
	TiO ₂		0,12	%		
	ZrO ₂		75,5	%		