

Refractory, CRM, Zircon-Zirconia, only available as set, please see JRRM-601-610, Powder

Art. ID JRRM-607
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		3,53	%		
	CaO		0,04	%		
	Fe ₂ O ₃		0,12	%		
	HfO ₂		1,21	%		
	K ₂ O		0,04	%		
	MgO	[1309-48-4]	0,03	%		
	Na ₂ O		0,02	%		
	P ₂ O ₅		0,08	%		
	SiO ₂		32,9	%		
	TiO ₂		0,13	%		
	ZrO ₂		61,6	%		