

Refractory, CRM, Zircon-Zirconia, only available as set, please see JRRM-601-610, Powder

Art. ID JRRM-608
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		0,7	%		
	CaO		0,52	%		
	Cr ₂ O ₃		0,49	%		
	Fe ₂ O ₃		0,09	%		
	HfO ₂		1,21	%		
	K ₂ O		0,01	%		
	MgO	[1309-48-4]	3,12	%		
	Na ₂ O		0,03	%		
	P ₂ O ₅		0,11	%		
	SiO ₂		34,6	%		
	TiO ₂		0,1	%		
	ZrO ₂		58,8	%		