

Refractory, CRM, Zircon-Zirconia, only available as set, please see JRRM-601-610, Powder

Art. ID JRRM-610
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Al ₂ O ₃		0,45	%		
	CaO		3,07	%		
	Fe ₂ O ₃		0,3	%		
	HfO ₂		0,98	%		
	K ₂ O		0,01	%		
	MgO	[1309-48-4]	0,54	%		
	Na ₂ O		0,04	%		
	P ₂ O ₅		0,11	%		
	SiO ₂		45,7	%		
	TiO ₂		0,09	%		
	ZrO ₂		48,7	%		