

Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder

Art. ID JRRM-701
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,09	%		
	Al ₂ O ₃		10,09	%		
	CaO		2,07	%		
	Cr ₂ O ₃		1,01	%		
	Fe ₂ O ₃		2	%		
	HfO ₂		0,85	%		
	K ₂ O		0,02	%		
	MgO	[1309-48-4]	0,47	%		
	Na ₂ O		1,84	%		
	P ₂ O ₅		~0,02	%		
	SiO ₂		28,44	%		
	TiO ₂		4,96	%		
	ZrO ₂		48,06	%		