

**Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder**

Art. ID JRRM-702  
Unit 20 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,18	%		
	Al <sub>2</sub> O <sub>3</sub>		38,14	%		
	CaO		1,55	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,11	%		
	Fe <sub>2</sub> O <sub>3</sub>		0,37	%		
	HfO <sub>2</sub>		2,08	%		
	K <sub>2</sub> O		0,57	%		
	MgO	[1309-48-4]	1,97	%		
	Na <sub>2</sub> O		2,02	%		
	P <sub>2</sub> O <sub>5</sub>		~0,02	%		
	SiO <sub>2</sub>		9,99	%		
	TiO <sub>2</sub>		0,21	%		
	ZrO <sub>2</sub>		42,54	%		