

Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder

Art. ID JRRM-702
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,18	%		
	Al ₂ O ₃		38,14	%		
	CaO		1,55	%		
	Cr ₂ O ₃		0,11	%		
	Fe ₂ O ₃		0,37	%		
	HfO ₂		2,08	%		
	K ₂ O		0,57	%		
	MgO	[1309-48-4]	1,97	%		
	Na ₂ O		2,02	%		
	P ₂ O ₅		~0,02	%		
	SiO ₂		9,99	%		
	TiO ₂		0,21	%		
	ZrO ₂		42,54	%		