

Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder

Art. ID JRRM-703
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,09	%		
	Al ₂ O ₃		46,34	%		
	CaO		0,03	%		
	Fe ₂ O ₃		0,05	%		
	HfO ₂		0,72	%		
	MgO	[1309-48-4]	0,01	%		
	Na ₂ O		0,53	%		
	P ₂ O ₅		~0,03	%		
	SiO ₂		14,64	%		
	TiO ₂		0,07	%		
	ZrO ₂		37,35	%		