

Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder

Art. ID JRRM-704
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,07	%		
	Al ₂ O ₃		19,58	%		
	CaO		0,15	%		
	Cr ₂ O ₃		0,51	%		
	Fe ₂ O ₃		0,55	%		
	HfO ₂		0,68	%		
	K ₂ O		1,4	%		
	MgO	[1309-48-4]	0,51	%		
	MnO		~0,08	%		
	Na ₂ O		0,22	%		
	P ₂ O ₅		~0,13	%		
	SiO ₂		42,61	%		
	TiO ₂		1,02	%		
	ZrO ₂		33,46	%		