

**Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder**

Art. ID JRRM-705  
Unit 20 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,16	%		
	Al <sub>2</sub> O <sub>3</sub>		64,14	%		
	CaO		0,19	%		
	Cr <sub>2</sub> O <sub>3</sub>		2,01	%		
	Fe <sub>2</sub> O <sub>3</sub>		0,14	%		
	HfO <sub>2</sub>		0,48	%		
	K <sub>2</sub> O		0,01	%		
	MgO	[1309-48-4]	0,46	%		
	Na <sub>2</sub> O		0,3	%		
	P <sub>2</sub> O <sub>5</sub>		~0,01	%		
	SiO <sub>2</sub>		1,99	%		
	TiO <sub>2</sub>		2,02	%		
	ZrO <sub>2</sub>		27,96	%		