

Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder

Art. ID JRRM-706
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,72	%		
	Al ₂ O ₃		25,95	%		
	CaO		1,58	%		
	Cr ₂ O ₃		0,01	%		
	Fe ₂ O ₃		0,13	%		
	HfO ₂		1,19	%		
	K ₂ O		0,95	%		
	MgO	[1309-48-4]	0,15	%		
	Na ₂ O		3,49	%		
	P ₂ O ₅		~0,01	%		
	SiO ₂		39,33	%		
	TiO ₂		3,77	%		
	ZrO ₂		22,72	%		