

Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder

Art. ID JRRM-707
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,01	%		
	Al ₂ O ₃		55,78	%		
	CaO		1,08	%		
	Cr ₂ O ₃		0,18	%		
	Fe ₂ O ₃		1,81	%		
	HfO ₂		0,36	%		
	K ₂ O		0,15	%		
	MgO	[1309-48-4]	0,84	%		
	Na ₂ O		0,19	%		
	P ₂ O ₅		~0,05	%		
	SiO ₂		21,17	%		
	TiO ₂		0,28	%		
	ZrO ₂		18,16	%		