

**Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder**

Art. ID JRRM-708  
Unit 20 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,13	%		
	Al <sub>2</sub> O <sub>3</sub>		79,52	%		
	CaO		1,17	%		
	Cr <sub>2</sub> O <sub>3</sub>		0,29	%		
	Fe <sub>2</sub> O <sub>3</sub>		0,8	%		
	HfO <sub>2</sub>		1,03	%		
	K <sub>2</sub> O		0,74	%		
	MgO	[1309-48-4]	1,64	%		
	Na <sub>2</sub> O		0,08	%		
	SiO <sub>2</sub>		0,54	%		
	TiO <sub>2</sub>		1,02	%		
	ZrO <sub>2</sub>		12,84	%		