

Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder

Art. ID JRRM-708
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,13	%		
	Al ₂ O ₃		79,52	%		
	CaO		1,17	%		
	Cr ₂ O ₃		0,29	%		
	Fe ₂ O ₃		0,8	%		
	HfO ₂		1,03	%		
	K ₂ O		0,74	%		
	MgO	[1309-48-4]	1,64	%		
	Na ₂ O		0,08	%		
	SiO ₂		0,54	%		
	TiO ₂		1,02	%		
	ZrO ₂		12,84	%		