

Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder

Art. ID JRRM-709
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|--------------------------------|-------------|---------------------|------|--------|--------|
| | Loss on Ignition (LOI) | | ~0,2 | % | | |
| | Al ₂ O ₃ | | 50,35 | % | | |
| | CaO | | 0,52 | % | | |
| | Cr ₂ O ₃ | | 2,91 | % | | |
| | Fe ₂ O ₃ | | 0,47 | % | | |
| | HfO ₂ | | 0,18 | % | | |
| | K ₂ O | | 0,21 | % | | |
| | MgO | [1309-48-4] | 1,2 | % | | |
| | Na ₂ O | | 1,03 | % | | |
| | SiO ₂ | | 34,38 | % | | |
| | TiO ₂ | | 0,09 | % | | |
| | ZrO ₂ | | 8,32 | % | | |