

Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder

Art. ID JRRM-709
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,2	%		
	Al ₂ O ₃		50,35	%		
	CaO		0,52	%		
	Cr ₂ O ₃		2,91	%		
	Fe ₂ O ₃		0,47	%		
	HfO ₂		0,18	%		
	K ₂ O		0,21	%		
	MgO	[1309-48-4]	1,2	%		
	Na ₂ O		1,03	%		
	SiO ₂		34,38	%		
	TiO ₂		0,09	%		
	ZrO ₂		8,32	%		