

**Refractory, CRM, Al-Zr-Si, only available as set, please see JRRM-701-710, Powder**

Art. ID JRRM-709  
Unit 20 g (powder)  
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,2	%		
	Al <sub>2</sub> O <sub>3</sub>		50,35	%		
	CaO		0,52	%		
	Cr <sub>2</sub> O <sub>3</sub>		2,91	%		
	Fe <sub>2</sub> O <sub>3</sub>		0,47	%		
	HfO <sub>2</sub>		0,18	%		
	K <sub>2</sub> O		0,21	%		
	MgO	[1309-48-4]	1,2	%		
	Na <sub>2</sub> O		1,03	%		
	SiO <sub>2</sub>		34,38	%		
	TiO <sub>2</sub>		0,09	%		
	ZrO <sub>2</sub>		8,32	%		