

Refractory, CRM, Alumina-Magnesia, only available as set, please see JRRM-801-810, Powder

Art. ID JRRM-802
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,06	%		
	Al ₂ O ₃		84,25	%		
	CaO		2	%		
	Fe ₂ O ₃		1,03	%		
	K ₂ O		0,46	%		
	MgO	[1309-48-4]	6,13	%		
	Na ₂ O		0,15	%		
	P ₂ O ₅		0,95	%		
	SiO ₂		3,32	%		
	TiO ₂		1,48	%		