

Refractory, CRM, Alumina-Magnesia, only available as set, please see JRRM-801-810, Powder

Art. ID JRRM-803
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,36	%		
	Al ₂ O ₃		74,23	%		
	CaO		0,57	%		
	Fe ₂ O ₃		4,9	%		
	MgO	[1309-48-4]	16,2	%		
	Na ₂ O		0,86	%		
	P ₂ O ₅		0,01	%		
	SiO ₂		0,58	%		
	TiO ₂		2,51	%		