

Refractory, CRM, Alumina-Magnesia, only available as set, please see JRRM-801-810, Powder

Art. ID JRRM-804
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,01	%		
	Al ₂ O ₃		64,66	%		
	CaO		4,76	%		
	Cr ₂ O ₃		~0,01	%		
	Fe ₂ O ₃		4,02	%		
	K ₂ O		0,04	%		
	MgO	[1309-48-4]	20,84	%		
	MnO		~0,02	%		
	Na ₂ O		0,08	%		
	P ₂ O ₅		0,11	%		
	SiO ₂		5,17	%		
	TiO ₂		0,13	%		