

Refractory, CRM, Alumina-Magnesia, only available as set, please see JRRM-801-810, Powder

Art. ID JRRM-805
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,17	%		
	Al ₂ O ₃		58,03	%		
	CaO		0,25	%		
	Fe ₂ O ₃		0,73	%		
	K ₂ O		0,01	%		
	MgO	[1309-48-4]	36,04	%		
	Na ₂ O		0,54	%		
	P ₂ O ₅		0,68	%		
	SiO ₂		2,49	%		
	TiO ₂		1,05	%		