

Refractory, CRM, Alumina-Magnesia, only available as set, please see JRRM-801-810, Powder

Art. ID JRRM-806
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,21	%		
	Al ₂ O ₃		48,85	%		
	CaO		0,97	%		
	Fe ₂ O ₃		0,16	%		
	MgO	[1309-48-4]	49,43	%		
	MnO		~0,02	%		
	Na ₂ O		0,04	%		
	P ₂ O ₅		0,04	%		
	SiO ₂		0,51	%		