

Refractory, CRM, Alumina-Magnesia, only available as set, please see JRRM-801-810, Powder

Art. ID JRRM-807
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,57	%		
	Al ₂ O ₃		39,96	%		
	CaO		2,75	%		
	Fe ₂ O ₃		0,32	%		
	K ₂ O		0,15	%		
	MgO	[1309-48-4]	55,07	%		
	Na ₂ O		0,32	%		
	P ₂ O ₅		0,53	%		
	SiO ₂		0,58	%		
	TiO ₂		0,19	%		