

Refractory, CRM, Alumina-Magnesia, only available as set, please see JRRM-801-810, Powder

Art. ID JRRM-809
Unit 20 g (powder)
Deliverydetails No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,48	%		
	Al ₂ O ₃		19,86	%		
	CaO		4,47	%		
	Fe ₂ O ₃		0,11	%		
	K ₂ O		0,98	%		
	MgO	[1309-48-4]	70,11	%		
	Na ₂ O		0,04	%		
	P ₂ O ₅		1,06	%		
	SiO ₂		0,36	%		
	TiO ₂		2,88	%		