

**Refractory, CRM, Alumina-Magnesia, only available as set, please see JRRM-801-810, Powder**

Art. ID                      JRRM-810  
Unit                         20 g (powder)  
Deliverydetails            No Dangerous Good /not restricted

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Loss on Ignition (LOI)		~0,22	%		
	Al <sub>2</sub> O <sub>3</sub>		10,08	%		
	CaO		0,18	%		
	Fe <sub>2</sub> O <sub>3</sub>		3,11	%		
	K <sub>2</sub> O		0,16	%		
	MgO	[1309-48-4]	78,96	%		
	MnO		~0,01	%		
	Na <sub>2</sub> O		0,75	%		
	P <sub>2</sub> O <sub>5</sub>		0,51	%		
	SiO <sub>2</sub>		4,21	%		
	TiO <sub>2</sub>		1,91	%		